DEEP CYCLE SERIES

DEEP CYCLE
PROFESSIONAL

PHYSICAL CHARACTERISTICS		
	SI Units	US Units
Length	244 mm	9,61 inch
Width	190 mm	7,48 inch
Height	274 mm	10,79 inch
Typical weight	29,40 kg	64,82 lbs

6V EU DC-240 Ah (C_{20})

Specifications:

- Nominal voltage: 6 V
- Rated capacity: 240 Ah (at C_{20} and 25 °C)
- Plate technology: Antimony / Antimony
- Separator: Polyethylene + glass mat
- Electrolyte: Sulphuric acid (SG 1,28) OCV 6.35V
- Standards: IEC 60254; IEC 61427
- Case / Lid material: Polypropylene
- Lid type: Flat
- Terminal type: Conical
- Carrying Handles: Available
- Cycles at 50% DoD: up to 900 cycles
- PVES applications: up to 2000 cycles

Performance characteristics:

BATTERY DISCHARGE PERFORMANCE AT 25°C				
Discharge rate	**C_5 (5 h)**	**C_{20} (20 h)**	**C_{100} (100 h)**	**Capacity at 25 A**
End of discharge voltage	5,10 V	5,25 V	5,40 V	5,25 V
Discharge capacity	197 Ah	240 Ah	265 Ah	505 min

Temperature correction factor of discharge C_5 (5 h) capacity							
Temperature	-10 °C	0 °C	20 °C	25 °C	30 °C	35 °C	40 °C
Correction factor	0.80	0.88	0.98	1.00	1.03	1.05	1.07

BATTERY CHARGE CONDITIONS AT 25oC

Charging profile: **Charge factor: 1.10 – 1.20**

IUIa –characteristics for flooded batteries



Charging times with IUIa-characteristics in hours at 25 °C



Stage1: Constant current **Stage 2**: Constant voltage **Stage 3**: Constant current

It is mandatory to check the electrolyte level every 3 months and top up with deionized water to the markings.

MONBAT Plc, 32A, Cherni vrah Blvd., fl. 4, 1407 Sofia, Bulgaria, tel: +359 2 962 11 50, fax:+359 2 962 11 46, e-mail: monbat.trading@monbat.com

BATTERY DISCHARGE CURVES AT 25oC

DISCHARGE PERFORMANCE AT CONSTANT CURRENT DISCHARGE (A)

.





It is mandatory to check the electrolyte level every 3 months and top up with deionized water to the markings.

MONBAT Plc, 32A, Cherni vrah Blvd., fl. 4, 1407 Sofia, Bulgaria, tel: +359 2 962 11 50, fax:+359 2 962 11 46, e-mail: monbat.trading@monbat.com